

1/1 WPAT - ©Derwent

- AN - 1989-243013 [34]
 XR - 1989-242941 1989-242984 1989-243015
 XA - C1989-108164
 XP - N1989-185233
 TI - Image forming method for silver halide colour films - comprises processing sequence of colour development, bleaching with soln. contg. ferric complex and fixing with soln. contg. thiocyanate
 DC - E19 G06 P83
 PA - (KONS) KONICA CORP
 IN - ISHIKAWA M; KOBOSHI I; KUSE S; KOBOSHI S
 NP - 4
 NC - 4
 PN - EP-329086 A 19890823 DW1989-34 Eng 120p *
 AP: 1989EP-0102526 19890214
 DSR: DE FR GB

 US5453348 A 19950926 DW1995-44 G03C-005/38 58p
 AP: 1989US-0309838 19890210; 1990US-0611487 19901101; 1993US-0066625 19930524; 1994US-0303239 19940908

 EP-329086 B1 19960124 DW1996-09 G03C-007/42 Eng 101p
 AP: 1989EP-0102526 19890214
 DSR: DE GB

 DE68925487 E 19960307 DW1996-15 G03C-007/42
 FD: Based on EP-329086
 AP: 1989DE-6025487 19890214; 1989EP-0102526 19890214
 PR - 1988JP-0048931 19880302; 1988JP-0032501 19880215
 CT - EP-255726; JP60140345; JP62222252
 2.Jnl.Ref; A3...9029; No-SR.Pub
 IC - G03C-005/38 G03C-007/42 G03C-005/395 G03C-007/34 G03C-007/44
 AB - EP-329086 A
 A new image forming method for silver halide colour materials comprises a processing sequence of colour development, bleaching, and fixing where the bleach soln. contains a ferric complex of cpd. (I) and the fix soln. contains at least one thiocyanate and an iodide present at not less than 0.5mol/l. In (I), A1, A2, A3 and A4 = same of different CH₂OH, COOM, or PO₃M₁M₂ M, M₁, and M₂ = H, Na, K or NH₄. X = subst. or unsubst. 3-6C alkylene.
 Specifically claimed are, (I-1) = (I) where A1, A2, A3, A4 = COOH and X = C₃H₆; (I-2) = (I) where A1, A2, A3, A4 = COOH and X = CH₂CHOHCH₂; (I-4) = (I) where A1, A2, A3, A4 = COOH and X = C₄H₈; and (I-7) = (I) where A1, A2, A3, A4 = PO₃H₂ and X = C₃H₆. Pref. (I) is present at 0.01-1.0, more pref. 0.05-0.4 mols/l bleach soln.. The pt. bleach soln. has pH value 2-8, more pref. 2-5.5. The fix soln. contains thiocyanate and iodide at 0.7-6, more pref. 1-5, most pref. 2-4 mols/l. Bleaching time is not more than 90, pref. 10-70, most pref. 20-55 seconds. Total time for bleaching and fixing is not more than 225 seconds, more pref. 20-200 seconds most pref. 40-180 seconds.
 ADVANTAGE - The process allows rapid processing with low stain in the unexposed areas. (0/0)
 MC - CPI: E05-G03C E05-G03D E05-L02A E31-B03C E32-B G06-G10 G06-G11 G06-H03 G06-H12
 UP - 1989-34
 UE - 1995-44; 1996-09; 1996-15